

TRANSPORT S.A.
Materials Technology

Page 2 of 2

Conclusion

All submitted samples of Luckylite HR Series Class 1 pressure sensitive retroreflective sheeting complied with the requirements of AS/NZS 1906.1:1993 in the areas of

Section 2.1.1 Minimum Photometric performance,

Section 2.1.2 Variation of performance with rotation angle

Section 2.2.2 Colour, Night time viewing

Section 2.2.1 (a) Colour Daytime viewing, chromaticity coordinates

The submitted red, yellow and white samples complied with section 2.2.1 (b) Colour, Daytime viewing, luminance factor.

The submitted green (NZ) and blue samples exhibited a luminance factor greater than the maximum set out in table 2.5 of AS/NZS 1906.1:1993



K. Simpson-Lyttle
TGO2 Optical/Paints
21/07/99